

## CEM-FIL® 70

### AR-GLASS CHOPPED STRANDS FOR RENDERING MORTARS



#### DESCRIPTION

- **Cem-FIL® 70** is a special purpose AR-glass fiber chopped strand designed for mixing with cement and other materials where a high degree of dispersion of the fibers is needed

#### BENEFITS

- Excellent workability
- Control and prevention of cracking in fresh concrete
- Improves the thixotropy of the mortar, making it easy to apply
- High dispersion: 100 million of filament per kg in fiber length 12 mm
- Safe and easy to handle
- Virtually invisible on the finished surface

#### APPLICATIONS

- **Cem-FIL® 70** product is typically used in the modification of specialist mortars and industrialized processes
- **Cem-FIL® 70** product chopped strands have a sizing system which is water dispersible, allowing full dispersion into individual filaments when mixing in an aqueous environment. It is mainly used in renders and mortars



# CEM-FIL® 70

## AR CHOPPED STRANDS FOR RENDERING MORTARS

### TECHNICAL CHARACTERISTICS

Fiber length	Filament Diameter (ISO 1888 : 2006)	Loss on Ignition (%) (ISO 1887 : 1995)	Moisture (%) (ISO 3344 : 1997)
3 – 6 – 9 – 12 mm / $\frac{1}{8}$ " – $\frac{1}{4}$ " – $\frac{3}{8}$ " – $\frac{1}{2}$ " inches	20 $\mu$ m / 0.00078"	0.60	0.50 max.

- Electrical Conductivity: Very low
- Specific Gravity: 2.68 g/cm<sup>3</sup>
- Material: Alkali Resistant Glass\*
- Softening point: 860°C – 1580°F
- Chemical Resistance: Very high
- Modulus of elasticity: 72 GPa – 10 x 10<sup>6</sup> psi
- Tensile Strength: 1000–1700 MPa – 145–250 x 10<sup>3</sup> psi

\* Our fibers are manufactured with high Zirconia content in compliance with ASTM C1666/C 1666/M-07 and EN 15422 and under the recommendations of PCI and GRCA

### DOSAGE

Recommended dosage is in between 0.02 to 0.2%, or 0.5 to 5 kg/m<sup>3</sup> (0.8 – 8 lb/cu.yd). Fibers can be blended and bagged with dry mortar ingredients, or introduced directly to the mixer at the facility or job site.

### PACKAGING AND STORAGE

Cem-FIL® 70 chopped strands are packed in individual plastic bags (18 kg). Cem-FIL® 70 chopped strands should be stored away from heat and moisture, and in their original packaging. Optimum conditions are temperature between 15°C and 35°C and humidity between 35% and 65%. If the product is stored at lower temperatures it is advisable to condition it in the workshop for at least 24 hours before use, to prevent condensation.

### QUALITY STANDARDS – CERTIFICATION

Cem-FIL® 70 fibers are manufactured under a quality Management System approved to ISO 9001.

Cem-FIL® fibers are not classified as dangerous by the Regulation 1272/2008/EC. For more information, please refer to our Safe Use Instructions Sheet.

**For further info please send a email to: [cem-fil@owenscorning.com](mailto:cem-fil@owenscorning.com) / [www.cem-fil.com](http://www.cem-fil.com)**

#### Americas

Owens Corning  
Composite Materials, LLC.  
One Owens Corning Parkway  
Toledo  
Ohio 43659  
1.800.get.pink™  
+1-623-566-0206

#### Europe

European Owens Corning  
Fiberglas Sprl.  
166 Chaussée de la Hulpe  
B-1170 Brussels  
Belgium  
+33.479.75.5300

#### Asia Pacific

Owens Corning - OC Asia Pacific  
Shanghai Regional Headquarters  
Unit 01, 02,05, 39/F,  
Pudong Kerry Parkside,  
1155 Fang Dian Road, Pudong, Shanghai,  
201204, China  
+86-21-6101 9666

This information and data contained herein is offered solely as a guide in the selection of reinforcement. The information contained in this publication is based on actual laboratory data and field test experience. We believe this information to be reliable, but do not guarantee its applicability to the user's process or assume any responsibility or liability arising out of its use or performance. The user agrees to be responsible for thoroughly testing any application to determine its suitability before committing to production. It is important for the user to determine the properties of its own commercial compounds when using this or any other reinforcement. Because of numerous factors affecting results, we make no warranty of any kind, express or implied, including those of merchantability and fitness for a particular purpose. Statements in this publication shall not be construed as representations or warranties or as inducements to infringe any patent or violate any law safety code or insurance regulation.

Owens Corning reserves the right to modify this document without prior notice.  
© 2014 Owens Corning. All Rights Reserved.

Pub number: 10010687-D. Cemfil\_70\_ww\_09\_2014\_Rev8\_EN. September 2014

[Cem-fil@owenscorning.com](mailto:Cem-fil@owenscorning.com)  
[www.cem-fil.com](http://www.cem-fil.com)