



M6X1

MAKE LARGE, THICK PARTS EASIER AND FASTER

M6X1 chopped strand mat represents a compelling solution for large and thick part manufacturing when high productivity is required in hand lay-up or closed mold processes.

- Produced with patented Advantex® corrosion resistant E-CR glass by Owens Corning.
- Made of medium tex multi-chop length strands bonded together with an emulsion binder.

Product Benefits

Easy handling and moldability

Optimized chop length mix provides superior dry tensile strength while bringing good conformability to contoured molds.

High process efficiency

Fast wet-through and low resin pick-up combined with excellent handling properties in dry and wet conditions. This makes the product an ideal choice for large and thick parts production with dry and wet-carrying process.

Enhanced service life

Compared to standard E-glass, Advantex® glass helps with enhanced service life in applications facing corrosion.

Application

M6X1 mat is designed for use with polyester, vinyl ester resin systems in hand lay-up or closed mold applications including automotive parts, boats, chemical tanks and pools.



Availability

M6X1 is available in Europe. Additional weights and widths are available upon request by your Owens Corning contact.

NOMINAL MAT WEIGHT (G/M ²)	ROLL WIDTH (CM)
225 - 300 - 450 - 600	95 - 125

Packaging and Labeling

Each roll is wound on a 76mm cardboard tube and placed inside a polyethylene bag and cardboard box. The boxed product is then placed vertically on a wooden pallet and shrink-wrapped for stability and protection.

Each roll bears a label detailing the product description, product code, nominal weight, roll width, roll number, and date of manufacture.

NOMINAL MAT WIDTH (CM)	ROLL DIAMETER (CM)	ROLLS PER PALLET	PALLET SIZE (CM)
95	30	12	127 x 97
125	30	12	127 x 97

Storage

Unless otherwise specified, it is recommended to store glass fiber products in a cool, dry area. Ideal conditions are at a temperature between 10°C and 35°C and a relative humidity between 35% and 85%. The glass fiber products must remain in their original packaging material until the point of usage. If the storage temperature is below 15°C, it is recommended that the product be stored in the workshop, within its original packaging, at least 24 hours prior to use to help prevent condensation. The packaging is not waterproof. Be sure to protect the product from the weather and other sources of water. When stored properly, there is no known shelf life to the product, and retesting is advised after three years from the initial production date to insure optimum performance.



Europe

European Owens Corning Fiberglas Sprl.

166 Chaussée de la Hulpe
B-1170 Brussels
Belgium
+32 3 674 8211

<https://www.owenscorning.com/composites> | Composites@owenscorning.com

This information and data contained herein is offered solely as a guide in the selection of product. We believe this information to be reliable, but do not guarantee its applicability to the user's process or assume any responsibility or liability arising out of its use or performance. The user agrees to be responsible for thoroughly testing any application of the product to determine its suitability. Because of numerous factors affecting results, we make no warranty of any kind, express or implied, including those of merchantability and fitness for a particular purpose. Statements in this publication shall not be construed as representations or warranties or as inducements to infringe any patent or violate any law, safety code or insurance regulation. We reserve the right to modify this document without prior notice.

Picture copyright: Istockphoto.com (bus); nostal6ie, shutterstock.com (tanks). Images for application illustration only.

Pub number: 10019337. M6X1_CSM_product data sheet_emea_10-2018_Rev2. January 2019. English.

THE PINK PANTHER™ & © 1964–2019 Metro-Goldwyn-Mayer Studios Inc. All Rights Reserved. © 2019 Owens Corning. All Rights Reserved.