



ASLAN™

ASLAN™ 600 FIBERGLAS™ DOWEL BARS

FOR LOAD TRANSFER IN CONCRETE SLABS

GLASS FIBER REINFORCED POLYMER (GFRP) DOWELS

Physical and Mechanical Properties


DOWEL DIAMETER		NOMINAL AREA		UNIT WEIGHT/ LENGTH		LONGITUDINAL SHEAR STRENGTH PER ASTM D4475 SHORT BEAM SHEAR		TRANSVERSE SHEAR STRENGTH PER ASTM D7617 DOUBLE SHEAR		TRANSVERSE SHEAR STRENGTH	
mm	in	mm ²	in ²	kg/m	lbs/ft	MPa	psi	MPa	psi	kN	lbs
16	5/8	198	0.307	0.447	0.30	42.1	6,100	151.7	22,000	30.0	6,754
19	3/4	285	0.442	0.566	0.38	46.9	6,800	151.7	22,000	43.3	9,724
25	1	507	0.785	0.967	0.65	58.6	8,500	151.7	22,000	76.8	17,270
32	1 1/4	792	1.227	1,563	1.05	58.6	8,500	151.7	22,000	120.1	26,994
38	1 1/2	1160	1.800	2,456	1.65	60.0	8,700	151.7	22,000	176.1	39,600

We reserve the right to make improvements in the product and/or process which may result in benefits or changes to some physical-mechanical characteristics. The data contained herein is considered representative of current production and is believed to be reliable and to represent the best available characterization of the product as of July 2011. Transverse shear test is per ASTM D7617 which has superseded the ACI 440.3R method B.4.

MATERIAL PROPERTIES per ASTM D7205-06	The "Shear Strength", typically the "Transverse" or "Double Shear" strength of the Aslan™ 600 Fiberglas™ Dowel product is determined using the ASTM D7617 method. "Longitudinal Shear" or "Short Beam Shear" subjects the bar to a three point loading fixture and measures the shear strength along the axis of the bar. This testing is performed per ASTM D4475.
GLASS FIBER CONTENT	> 70% by weight per ASTM D2584
MOISTURE ABSORPTION	24 hour absorption at 122°F (50°C) ≤ 0.25%, per ASTM D570
SEALING OF ENDS	Not necessary
GREASING OF FRP DOWELS	Not necessary
TRANSITION TEMPERATURE OF RESIN T_g	> 230°F (110°C) per DSC method
APPLICATIONS	<ul style="list-style-type: none"> • High speed tollways • Jointed concrete paving

Aslan™ 600 Fibreglas™ Dowel

HB PART NUMBER	CONCRETE THICKNESS		DOWEL HEIGHT		DOWEL SPACING	
	mm	in	mm	in	cm	in
DBB1500-12-5	254	10	127	5	305	12
DBB1500-10-6	305	12	152	6	254	10



Handling and Placement

Field cutting of Aslan™ 600 Fibreglas™ Dowels is generally not necessary. However, if required use a fine blade saw, grinder, carborundum or diamond blade. We use a diamond blade in wet bath for cutting the dowels. Sealing of Aslan™ 600 Fibreglas™ Dowel ends is NOT necessary. Greasing of Aslan™ 600 Fibreglas™ Dowels is NOT necessary (the bond strength to concrete is sufficiently low.)

When installing Dowels in the DBB1500-10-6 basket:

The following high strength structural adhesives are recommended for use.

- Press fit the Dowel into the opening.
- Tap the dowel into the basket from the end to secure the dowel into place.
- Attach the Dowels and baskets to the runners as required.



Owens Corning Composite Materials, LLC.

One Owens Corning Parkway
Toledo, Ohio, USA 43659
1-800-GET-PINK®

<https://www.owenscorning.com/rebar>

This information and data contained herein is offered solely as a guide in the selection of product. We believe this information to be reliable, but do not guarantee its applicability to the user's process or assume any responsibility or liability arising out of its use or performance. The user agrees to be responsible for thoroughly testing any application of the product to determine its suitability. Because of numerous factors affecting results, we make no warranty of any kind, express or implied, including those of merchantability and fitness for a particular purpose. Statements in this publication shall not be construed as representations or warranties or as inducements to infringe any patent or violate any law, safety code or insurance regulation. We reserve the right to modify this document without prior notice.

Pub. 10022293 – Owens Corning® Aslan™ 600 Fibreglas™ Dowel Data Sheet_ww_01-2018_Rev1_EN. July 2020

THE PINK PANTHER™ & © 1964–2020 Metro-Goldwyn-Mayer Studios Inc. All Rights Reserved. © 2020 Owens Corning. All Rights Reserved.