



905A-AB SMC FOR VINYL ESTER & POLYESTER

High-performance for fast wet through and good density.

905A-AB is a reinforcement for Sheet Molding Compound (SMC), which offers improved processing over conventional products in vinyl ester resins and where fast wet through and good sheet density are required.

- Made from Advantex® glass.
- Compatible with polyester and vinyl ester resin systems.
- Manufactured from a collection of continuous glass filaments, gathered, without mechanical twists, into a split strand.

Product Benefits

Excellent processability

- Good impregnation and wet-through characteristics enable 10-65% glass loading, easy unwinding and chopping, flat lay-down & uniform dispersion with low fuzz and static.

Great Mechanical Properties and Class A Auto Surface

- Good product flow within mold, along with desirable wet-through characteristics allow lower sheet density and low sheet squeeze out, resulting in complex decorative contours, excellent mechanical properties, a Class A automotive surface and high stiffness in the final part.

Enhanced Service Life

- Advantex® glass helps fight corrosion, enhancing service life compared to standard E-glass.

Applications

905A-AB roving is designed for a wide variety of SMC applications, automotive and recreational structural applications and housings, as well as business equipment.

Availability

905A-AB is available in North America. Other Tex may be available upon request.

MANUFACTURING REGION	PRODUCT/DOFF DESCRIPTION	EXTERNAL Ø (IN)	HEIGHT (IN)	NET WEIGHT (LB)
North America	905A-AB 4500 Tex	14	10.3	67.5

Technical Characteristics (Nominal Values)

LINEAR WEIGHT OF ROVING (TEX) (KG/KM)	YIELDS (YDS/LB)	LOSS ON IGNITION (%) ISO 1887:2014
4500	110	1.73 nom

Packaging & Labeling (Standard Reference)

Each bobbin is protected by a plastic film (Tack-Pak®). Please do not remove film during use. Creel-Pak® packaging is available upon request.

Each bobbin has a self-adhesive identification label, showing the product reference and the production date. Each pallet has at least one identification label detailing the product reference, pallet net and gross weights, production date and pallet production code. The packaging system is designed to allow short term stacking of two pallets. When stacking two high, care should be taken to correctly and smoothly place the top pallet. It is recommended to use a plywood plate between the two pallets in order not to damage the lower pallet.

MANUFACTURING REGION	PRODUCT	DOFF Ø (IN)	PALLET DIM. LxWxH (IN)	LAYERS PER PALLET	DOFFS PER LAYER	NUMBER OF ENDS	PALLET NET WEIGHT (LB)
North America	905A-AB 4500 Tex	14	56 x 43 x 47	4	12	12	3,240

Storage

It is generally recommended to store glass fiber products in original packaging in a cool dry area, preferably 60°F-80°F with relative humidity between 35% and 75%. Under such conditions, the 905A-AB roving can be used up to 2 years from the date of manufacture. After 2 years, it is recommended to check product quality before use. The packaging system is designed to allow short term stacking of two pallets (maximum). When stacking two high, care should be taken to correctly and smoothly place the top pallet. It is recommended to use a plywood plate between the two pallets in order not to damage the lower pallet.



Americas

Owens Corning Composite Materials, LLC.

One Owens Corning Parkway
Toledo, Ohio, USA 43659
1-800-GET-PINK®

<https://www.owenscorning.com/composites> | Composites@owenscorning.com

This information and data contained herein is offered solely as a guide in the selection of product. We believe this information to be reliable, but do not guarantee its applicability to the user's process or assume any responsibility or liability arising out of its use or performance. The user agrees to be responsible for thoroughly testing any application of the product to determine its suitability. Because of numerous factors affecting results, we make no warranty of any kind, express or implied, including those of merchantability and fitness for a particular purpose. Statements in this publication shall not be construed as representations or warranties or as inducements to infringe any patent or violate any law, safety code or insurance regulation. We reserve the right to modify this document without prior notice.

Image copyright: leonello calvetti / shutterstock.com, image for application illustration only.

Pub number: 10023630. 905A-AB_MER_product data sheet_na_07-2019_Rev0. July 2019. English.

THE PINK PANTHER™ & © 1964–2019 Metro-Goldwyn-Mayer Studios Inc. All Rights Reserved. © 2019 Owens Corning. All Rights Reserved.