



SE1200 VERSATILITY FOR BROAD APPLICATIONS

SE1200 single-end Type 30™ roving is a compelling solution designed specifically for knitting and weaving with versatility to work well in filament winding, pultrusion, and LFTP applications.

- Produced with Advantex® corrosion resistant E-CR glass by Owens Corning.
- Compatible with polyester, vinyl ester, epoxy, and polyurethane resins.

Product Benefits

Excellent Processing

Smooth run-out from lower drag across contact points produces less fuzz, resulting in smoother parts, less clean-up, and improved machine efficiencies.

Multiprocess and Multi-resin Compatible

Flexibility for use with standard weaving looms, multiaxial knitting machines, filament winding, and pultrusion.

Fast Wet-out with Reduced Cost

Fast, uniform strand wet-out leads to higher glass loading and good adhesion, resulting in optimized part production speed which supports increased productivity and better-quality finished parts.

Enhanced Service Life

Compared to standard E-glass, Advantex® glass provides longer service life in applications facing corrosion and possesses high fatigue properties to help qualify for wind energy.

Application

SE1200 is designed for use in the manufacture of knitted or woven glass fabrics used for transportation applications, pultruded central strength members for fiber optic cabling, filament wound pipe, and tanks for liquid transport or energy storage.

Technical
Characteristics

The following data was generated using production material SE1200 – 735 Tex (675 Yield).

MECHANICAL PROPERTIES SE1200 - 734 TEX (675 YIELD)	STRAND TENSILES: ASTM D2343		INTERLAMINAR SHEAR STRENGTH NOL RING: ASTM D2344		
	STRENGTH (MPA)	STRENGTH (KSI)	DRY SHEAR STRENGTH (MPA)	DRY SHEAR STRENGTH (PSI)	SHEAR STRENGTH RETENTION 72 HR BOIL (%)
Anhydride/DER 331 Epoxy Resin	2700	395	66.3	9620	99%
Polyester F701 Resin	2570	375	73.4	10650	85%

Availability &
Packaging

SE1200 is manufactured in North America, South America, Europe and Asia Pacific. Not all Tex are available in all regions. Please consult with your Owens Corning representative for additional information.

TEX	YIELD
100 – 200 – 275 – 300 – 320 – 385 – 410 – 480 – 600	4961 – 4965 – 2480 – 1805 – 1654 – 1550 – 1288 – 1210 – 1033 – 827
735 – 900 – 1100 – 1150 – 1200 – 1500 – 1800 – 2000	827 – 675 – 551 – 451 – 450 – 431 – 413 – 330 – 276 – 248
2000 – 2200 – 2400 – 4400 – 4800 – 8800 – 9600	250 – 225 – 207 – 113 – 103 – 56 – 52

Rovings are available in a single-end internal-pull package. Pallets are stretch wrapped for load stability. Each doff is wrapped for protection and to aid strand runout and transfer. Pallets are available in bulk or Creel-Pak™ pallet packaging format, depending on region.

Labeling

Each individual package is labeled with information including: product name, Tex/yield, producing plant, and production date.

Storage

It is recommended to store glass fiber products in a cool, dry area. The glass fiber products must remain in their original packaging material until the point of usage; the product should be stored in the workshop, within its original packaging, 48 hours prior to its utilization, to allow it to reach the workshop temperature condition and prevent condensation, especially during the cold season. The packaging is not waterproof. Be sure to protect the product from the weather and other sources of water.

When stored properly, there is no known shelf life to the product, but retesting is advised after three years from the initial production date to ensure optimum performance.

The packaging system is designed to allow stacking of two pallets. When stacking pallets two high, care should be taken to place the top pallet gently and align properly. Owens Corning is not responsible for any damage resulting from stacking pallets more than two high.



Americas

**Owens Corning Composite
Materials, LLC.**
One Owens Corning Parkway
Toledo, OH 43659 USA
1-800-GET-PINK®

Europe

**European Owens Corning
Fiberglass Sprl.**
166 Chaussée de la Hulpe
B-1170 Brussels
Belgium
+32 3 674 8211

Asia Pacific

**Owens Corning Shanghai
Regional Headquarters**
40/F, Pudong Kerry Parkside,
115 Fang Dian Road, Pudong,
Shanghai, 201204, China
+86-21-6101 9666

<https://www.owenscorning.com/composites> | Composites@owenscorning.com

This information and data contained herein is offered solely as a guide in the selection of product. We believe this information to be reliable, but do not guarantee its applicability to the user's process or assume any responsibility or liability arising out of its use or performance. The user agrees to be responsible for thoroughly testing any application of the product to determine its suitability. Because of numerous factors affecting results, we make no warranty of any kind, express or implied, including those of merchantability and fitness for a particular purpose. Statements in this publication shall not be construed as representations or warranties or as inducements to infringe any patent or violate any law, safety code or insurance regulation. We reserve the right to modify this document without prior notice.

Pub. No. 10023879-B, November 2024.
THE PINK PANTHER™ & © 1964–2024 Metro-Goldwyn-Mayer Studios Inc. All Rights Reserved. © 2024 Owens Corning. All Rights Reserved.