

VL9202 SURFACING NONWOVENS

VL9202 is composed of chopped filaments of Advantex® glass fiber, 16 microns in diameter, that are bonded together with a styrene insoluble binder system designed for pultrusion processes. Surfacing veil creates and strengthens the resin-rich surface of the composite part, providing a strong bond and enhancing the surface appearance by masking the coarse reinforcing fiber pattern.

• Flexible and conformable to accommodate the process challenges associated with custom complex profiles.

PULTRUSION VEIL AT 3/8, 1/2 AND 1 OZ/FT²

Product Benefits

- Corrosion resistance, long-term durability, thanks to Advantex® E-CR glass.
- · Easy resin wet-out.
- · High-quality, uniform surface layer.
- · Enhanced part structural strength.
- · High flexibility for complex die processing.

Applications

- · Residential windows/doors frames and decking.
- Industrial and consumer good handles.
- · Commercial curtain wall frames.
- Composite parts for commercial construction.
- · Electrical flat sheet panels.





Technical Characteristics (Nominal Values)

PROPERTY		TEST METHOD	SPECIFICATION NOMINAL
	(lb/csf)		3.1
Area Weight	(g/m^2)	TAPPI T - 410	152
	$(oz/ft^{2)}$		0.50
MD Tensile Strength	(lb/2-in)	TAPPI T – 494	50
MD Tensile Strength	(N/50 mm)	TAPPI T – 494	220
CD Tensile Strength	(lb/2-in)	TAPPI T – 494	35
CD Tensile Strength	(N/50 mm)	TAPPI T – 494	155
Tensile Strength Ratio		TAPPI T – 494	1.5
Thickness	(Mil/mm)	-	58/1.47
Gurley Stiffness	(mg-force)	-	4500



Americas

Owens Corning Composite Materials, LLC.

One Owens Corning Parkway Toledo, Ohio, USA 43659 1-800-GET-PINK®

Europe

European Owens Corning Fiberglas Sprl.

166 Chaussée de la Hulpe B-1170 Brussels Belgium +32 3 674 8211

Asia Pacific

Owens Corning Shanghai Regional Headquarters

40/F, Pudong Kerry Parkside, 115 Fang Dian Road, Pudong, Shanghai, 201204, China +86-21-6101 9666

https://www.owenscorning.com/composites | Composites@owenscorning.com

This information and data contained herein is offered solely as a guide in the selection of product. We believe this information to be reliable, but do not guarantee its applicability to the user's process or assume any responsibility or liability arising out of its use or performance. The user agrees to be responsible for thoroughly testing any application of the product to determine its suitability. Because of numerous factors affecting results, we make no warranty of any kind, express or implied, including those of merchantability and fitness for a particular purpose. Statements in this publication shall not be construed as representations or warranties or as inducements to infringe any patent or violate any law, safety code or insurance regulation. We reserve the right to modify this document without prior notice.