



FOAMULAR® 150 RIGID FOAM INSULATION

EXTRUDED POLYSTYRENE (XPS) RIGID FOAM INSULATION

Owens Corning® FOAMULAR® 150 Extruded Polystyrene XPS Rigid Foam Insulation is a closed cell, moisture-resistant rigid foam board well suited to meet the need for a wide variety of building applications.¹ FOAMULAR® 150 Extruded Polystyrene XPS Rigid Foam Insulation is great for many residential and commercial construction above grade applications such as wall furring, cavity wall, crawl spaces, sheathing and other applications.¹


Features



**SUPERIOR
MOISTURE
RESISTANCE**



DURABLE



**EASY TO CUT,
FORM, & FIT**

Applications

- FOAMULAR® 150 is an ideal product for insulating crawlspace walls because FOAMULAR® boards are easy to handle and installation is not difficult. Crawlspaces may not require a fire barrier; check your local codes for requirements.
- Offers a weather resistant barrier (when joints are sealed) to enhance the building resistance to air and moisture penetration.
- Delivers R-5 per inch insulation to interior basement walls. FOAMULAR® cannot be left exposed in a basement and must be covered by a thermal barrier, such as gypsum drywall, that is at least 1/2" thick.

Standards, Codes Compliance

- Meets ASTM C578 Type X
- UL Classification Certificate U-197
- Code Evaluation Report UL ER8811-01
- ASTM E119 Fire Resistance Rated Wall Assemblies³
- Meets California Quality Standards; HUD UM #71a
- Compliance verification by RADCO (AA-650)



Physical Properties¹

PROPERTY	TEST METHOD ²	VALUE	
Thermal Resistance³ , R-Value, hr·ft ² ·°F/Btu (RSI, °C·m ² /W) @ 75°F (24°C) mean temperature	ASTM C518	5.0 (0.88)	
		@ 40°F (4.4°C) mean temperature	5.4 (0.95)
		@ 25°F (-3.9°C) mean temperature	5.6 (0.99)
Long Term Thermal Resistance , LTTR-Value ³ , minimum hr·ft ² ·°F/Btu (RSI, °C·m ² /W) @ 75°F (24°C) mean temperature	CAN/ ULC S770-03	5.0 (0.88)	
Compressive Strength⁴ , minimum psi (kPa)	ASTM D1621	15 (104)	
Flexural Strength⁵ , minimum psi (kPa)	ASTM C203	40 (276)	
Water Absorption⁶ , maximum % by volume	ASTM C272	0.03	
Water Vapor Permeance⁷ , maximum perm (ng/Pa·s·m ²)	ASTM E96	1.5 (86)	
Dimensional Stability , maximum % linear change	ASTM D2126	2.0	
Flame Spread^{8,9}	ASTM E84	10	
Smoke Developed^{8,9}	ASTM E84	175	
Oxygen Index⁸ , minimum % by volume	ASTM D2863	24	
Service Temperature , maximum °F (°C)	-	165 (74)	
Linear Coefficient of Thermal Expansion , in/in/°F (m/m/°C)	ASTM E228	3.5 x 10 ⁻⁵ (6.3 x 10 ⁻⁵)	

1. Properties shown are representative values for 1" thick material, unless otherwise specified.
2. Modified as required to meet ASTM C578
3. R means the resistance to heat flow; the higher the value, the greater the insulation power. This insulation must be installed properly to get the marked R-value. Follow the manufacturer's instructions carefully. If a manufacturer's fact sheet is not provided with the material shipment, request this and review it carefully. R-values vary depending on many factors including the mean temperature at which the test is conducted, and the age of the sample at the time of testing. The U.S. FTC requires the R-value of home insulation to be measured at 75 degrees F mean temperature. R-value claims should always be compare at the same Mean Temperature. Because rigid foam plastic insulation products are not all aged in accordance with the same standards, it is useful to publish comparison R-value data. The R-value for FOAMULAR® XPS Insulation is provided from testing at three mean temperatures, 25°F, 40°F and 75°F, and from two aging (conditioning) techniques, 180 day real-time aged (as mandated by ASTM C578) and a method of accelerated aging sometimes called "Long Term Thermal Resistance" (LTTR) per CAN/ULC S770-03.
4. Values at yield or 10% deflection, whichever occurs first.
5. Value at yield or 5%, whichever occurs first.
6. Data ranges from 0.00 to value shown due to the level of precision of the test method.
7. Water vapor permeance decreases as thickness increases.
8. These laboratory tests are not intended to describe the hazards presented by this material under actual fire conditions.
9. Data from Underwriters Laboratories Inc.® classified. See Classification Certificate U-197.

1. Not for use in flat or low slope roofing. For low slope roofing applications, use FOAMULAR® THERMAPINK® Extruded Polystyrene (XPS) Rigid Foam Insulation.
 2. R means the resistance to heat flow; the higher the R-value, the greater the insulating power.
 3. Visit www.owenscorning.com for more details.

Product and Packaging Data¹

MATERIAL

Extruded polystyrene closed cell foam, ASTM C578 Type X, 15 psi minimum

PACKAGING

Shipped in poly-wrapped units with individually wrapped or banded bundles.

THICKNESS (IN)	PRODUCT DIMENSIONS (IN) X WIDTH (IN) X LENGTH (IN)	PALLET (UNIT) DIMENSIONS (TYPICAL) WIDTH (FT) X LENGTH (FT) X HEIGHT (FT)	SQUARE FEET PER PALLET	BOARD FEET PER PALLET	BUNDLES PER PALLET	PIECES PER BUNDLE	PIECES PER PALLET	EDGES
1	1 x 24 x 96	4 x 8 x 8	3,072	3,072	8	24	192	Square Edge, Scored Square Edge, Tongue & Groove
	1 x 24 x 96	4 x 8 x 8	3,072	3,072	8	24	192	
	1 x 48 x 96	4 x 8 x 8	3,072	3,072	8	12	96	
	1 x 48 x 96 (Half unit)	4 x 8 x 8	1,536	1,536	4	12	48	
	1 x 48 x 108	4 x 9 x 8	3,456	3,456	8	12	96	
1½	1.5 x 24 x 96	4 x 8 x 8	2,048	3,072	8	16	128	
	1.5 x 48 x 96	4 x 8 x 8	2,048	3,072	8	8	64	
2	2 x 24 x 96	4 x 8 x 8	1,536	3,072	8	12	96	
	2 x 48 x 96	4 x 8 x 8	1,536	3,072	8	6	48	
2½	2.5 x 48 x 96	4 x 8 x 8	1,152	2,830	4	9	36	
3	3 x 24 x 96	4 x 8 x 8	1,024	3,072	8	8	64	
	3 x 48 x 96	4 x 8 x 8	1,024	3,072	8	4	32	

1. Available lengths and edge configurations vary by thickness. See www.foamular.com for current offerings. Other sizes may be available upon request. Consult your local Owens Corning representative for availability.

Technical Information

- FOAMULAR® 150 Extruded Polystyrene XPS Rigid Foam Insulation is a non-structural material.
- FOAMULAR® 150 XPS Insulation can be left exposed for up to 60 days. During that time some degradation or “dusting” of the polystyrene surface may begin. Once covered, the deterioration stops.
- FOAMULAR® 150 Extruded Polystyrene XPS Rigid Foam Insulation has a maximum service temperature of 165°F. For horizontal applications, always turn the black print side down. Do not cover FOAMULAR® XPS Insulation either stored (factory wrapped or unwrapped), or partially installed, with dark colored (non-white), or clear (non-opaque) coverings and leave it exposed to the sun. See Owens Corning publication number 10015704, “Heat Build Up Due to Solar Exposure” for more information.
- This product is combustible. A protective barrier or thermal barrier is required as specified in the appropriate building code. For additional information, contact Owens Corning World Headquarters at 1-800-GET-PINK®.
- All construction should be evaluated for the necessity to provide vapor retarders. See current ASHRAE Handbook of Fundamentals.

Limited Warranty

FOAMULAR® XPS Insulation limited lifetime warranty maintains 90% of its R-value for the lifetime of the building and covers all ASTM C578 properties. See actual warranty for complete details, limitations and requirements at www.owenscorning.com.

Environmental and Sustainability

Owens Corning is a worldwide leader in building material systems, insulation and composite solutions, delivering a broad range of high-quality products and services. Owens Corning is committed to driving sustainability by delivering solutions, transforming markets and enhancing lives. More information can be found at www.owenscorning.com.

Certifications and Sustainable Features

- Certified by SCS Global Services to contain a minimum of 20% recycled content pre-consumer
- GREENGUARD Certified products are certified to GREENGUARD standards for low chemical emissions into indoor air during product usage. For more information, visit ul.com/gg
- Environmental Product Declaration (EPD) has been certified by UL Environment
- Utilizing FOAMULAR® XPS insulation can help builders achieve green building certifications including the U.S. Green Building Council’s Leadership in Energy and Environmental Design (LEED®) certification



Disclaimer of Liability

Technical information contained herein is furnished without charge or obligation and is given and accepted at recipient’s sole risk. Because conditions of use may vary and are beyond our control, Owens Corning makes no representation about, and is not responsible or liable for the accuracy or reliability of data associated with particular uses of any product described herein. SCS Global Services provides independent verification of recycled content in building materials and verifies recycled content claims made by manufacturers. For more information, visit www.SCSglobalservices.com.

LEED® is a registered trademark of the U.S. Green Building Council.

Notes

For additional information, refer to the Safe Use Instruction Sheet (SUIS) found in the SDS Database via <http://sds.owenscorning.com>.

OWENS CORNING INSULATING SYSTEMS, LLC

ONE OWENS CORNING PARKWAY TOLEDO, OHIO 43659

1-800-GET-PINK®

www.owenscorning.com

Pub. No. 23513-M. Printed in U.S.A. Jan. 2020. THE PINK PANTHER™ & © 1964–2020 Metro-Goldwyn-Mayer Studios Inc. All Rights Reserved. The color PINK is a registered trademark of Owens Corning. © 2020 Owens Corning. All Rights Reserved.