



FOAMULAR® & FOAMULAR® NGX™ 250

EXTRUDED POLYSTYRENE (XPS) RIGID FOAM INSULATION

Owens Corning® FOAMULAR® & FOAMULAR® NGX™ 250 Extruded Polystyrene (XPS) Insulation are closed-cell, moisture-resistant rigid foam boards well suited to meet the needs of a wide variety of building applications.¹ Both products are great for above-and below-grade residential and commercial applications such as perimeter/foundation, cavity wall, precast concrete, under slab, and other applications.

FOAMULAR® NGX™ 250 contains the additional benefit of being manufactured with a blowing agent formulation that delivers a 90% reduction to Global Warming Potential (100 year), including the complete elimination of HFC 134a.²

- 1 Not for use in flat or low slope roofing. For low slope roofing applications, use FOAMULAR® & FOAMULAR® NGX™ THERMAPINK® or FOAMULAR® & FOAMULAR® NGX™ 400/600/1000 Extruded Polystyrene (XPS) Rigid Foam Insulation.
- 2 Compared to FOAMULAR® 250 blowing agent formulation.


Features



SUPERIOR MOISTURE RESISTANCE



DURABLE



EASY TO CUT, FORM & FIT

Standards, Codes Compliance

- Meets ASTM C578 Type IV
- UL Classification Certificate U-197
- Code Evaluation Report UL ER8811-01
- ASTM E119 Fire Resistance Rated Wall Assemblies³
- Meets California Quality Standards; HUD UM #71a

³ Visit www.owenscorning.com for more details

Applications

- Under slabs
- Perimeter/Foundation walls
- Cavity walls
- Precast walls
- Weather-resistant barrier (when joints are sealed)

Physical Properties⁴

PROPERTY	TEST METHOD ⁵	VALUE
Thermal Resistance, ⁶ R-Value, hr·ft ² ·°F/Btu (RSI, °C·m ² /W) @ 75°F (24°C) mean temperature	ASTM C518	5.0 (0.88)
@ 40°F (4.4°C) mean temperature		5.4 (0.95)
@ 25°F (-3.9°C) mean temperature		5.6 (0.99)
Long-Term Thermal Resistance, LTTR-Value ⁷ , minimum hr·ft ² ·°F/Btu (RSI, °C·m ² /W) @ 75°F (24°C) mean temperature	CAN/ULC S770-03	5.0 (0.88)
Compressive Strength ⁷ , minimum psi (kPa)	ASTM D1621	25 (172)
Flexural Strength ⁸ , minimum psi (kPa)	ASTM C203	50 (345)
Water Absorption ⁹ , maximum % by volume	ASTM C272	0.3
Water Vapor Permeance ¹⁰ , maximum perm (ng/Pa·s·m ²)	ASTM E96	1.5 (86)
Dimensional Stability, maximum % linear change	ASTM D2126	2.0
Flame Spread ^{11, 12}	ASTM E84	10
Smoke Developed ^{11, 12}	ASTM E84	175
Oxygen Index ¹¹ , minimum % by volume	ASTM D2863	24
Service Temperature, maximum °F (°C)	-	165 (74)
Linear Coefficient of Thermal Expansion, in/in/°F (m/m/°C)	ASTM E228	3.5 x 10 ⁻⁵ (6.3 x 10 ⁻⁵)

- 4 Properties shown are representative values for 1" thick material, unless otherwise specified.
- 5 Modified as required to meet ASTM C578.
- 6 R means the resistance to heat flow, the higher the value, the greater the insulation power. This insulation must be installed properly to get the marked R-value. Follow the manufacturer's instructions carefully. If a manufacturer's fact sheet is not provided with the material shipment, request this and review it carefully. R-values vary depending on many factors, including the mean temperature at which the test is conducted and the age of the sample at the time of testing. The U.S. FTC requires the R-value of home insulation to be measured at 75 degrees F mean temperature. R-value claims should always be compare at the same mean temperature. Because rigid foam plastic insulation products are not all aged in accordance with the same standards, it is useful to publish comparison R-value data. The R-value for FOAMULAR® & FOAMULAR® NGX™ XPS Insulation is provided from testing at mean temperatures of: -4°C (25°F), 4.4°C (40°F), and 24°C (75°F) and aging techniques of 180-day real time aged (as mandated by ASTM C578) and accelerated aging "Long-Term Thermal Resistance" (LTTR) per CAN/ULC S770-03.
- 7 Values at yield or 10% deflection, whichever occurs first.
- 8 Value at yield or 5%, whichever occurs first.
- 9 Data ranges from 0.00 to value shown due to the level of precision of the test method.
- 10 Water vapor permeance decreases as thickness increases.
- 11 These laboratory tests are not intended to describe the hazards presented by this material under actual fire conditions.
- 12 Data from Underwriters Laboratories Inc.® classified. See Classification Certificate U-197.

Technical Information

- FOAMULAR® & FOAMULAR® NGX™ XPS insulation are non-structural materials and must be installed on framing that is independently braced and structurally adequate to meet required construction and service loading conditions.
- FOAMULAR® & FOAMULAR® NGX™ XPS insulation can be exposed to the exterior during normal construction cycles. During that time, some fading of color may begin due to UV exposure, and if exposed for extended periods of time, some degradation or “dusting” of the polystyrene surface may begin. It is best if the product is covered within 60 days to minimize degradation. Once covered, the deterioration stops, and damage is limited to the thin top surface layers of cells. Cells below are generally unharmed and still useful insulation.
- FOAMULAR® & FOAMULAR® NGX™ XPS insulation have a maximum service temperature of 165°F. Install only as much FOAMULAR® & FOAMULAR® NGX™ XPS insulation as can be covered in the same day. For horizontal applications, always turn the print side down so the black print does not show to the sun, which may at times act as a solar collector, raising the temperature of the foam under the print to an unacceptable level.
- Do not cover FOAMULAR® or FOAMULAR® NGX™ XPS insulation either stored (factory wrapped or unwrapped), or partially installed, with dark colored (non-white), or clear (non-opaque) coverings and leave it exposed to the sun. Examples of such coverings include but are not limited to filter fabrics, membranes, temporary tarps, clear polyethylene, etc. If improperly covered and exposed to the right combination of sun, time and temperature, FOAMULAR® and FOAMULAR® NGX™ XPS insulation deformation damage may occur rapidly. See Owens Corning publication “Heat Build Up Due to Solar Exposure Technical Bulletin” (Pub. No. 10015704) for more information.
- This product is combustible. A protective barrier or thermal barrier is required to separate this product from interior living or conditioned spaces as specified in the appropriate building code.
- All construction should be evaluated for the necessity to provide vapor retarders. See current ASHRAE Handbook of Fundamentals.

Certifications and Sustainable Features

- Certified by SCS Global Services to contain a minimum of 20% recycled content pre-consumer
- GREENGUARD Certified products are certified to GREENGUARD standards for low chemical emissions into indoor air during product usage. For more information, visit ul.com/gg
- Environmental Product Declaration (EPD) has been certified by UL Environment
- Qualified as an ENERGY STAR® product, under the U.S. Environmental Protection Agency and the U.S. Department of Energy
- Utilizing FOAMULAR® & FOAMULAR® NGX™ XPS insulation can help builders achieve green building certifications including the U.S. Green Building Council’s Leadership in Energy and Environmental Design (LEED®) certification



Environmental and Sustainability

Owens Corning is a worldwide leader in building material systems, insulation and composite solutions, delivering a broad range of high-quality products and services. Owens Corning is committed to driving sustainability by delivering solutions, transforming markets and enhancing lives. More information can be found at www.owenscorning.com.

FOAMULAR® is manufactured with a polystyrene resin and blend of HFC blowing agents that have a global warming potential (100 year) of less than 750.

FOAMULAR® NGX™ is manufactured with a polystyrene resin and a blend of HFO and HFC blowing agents that have a global warming potential (100 year) of less than 80.

Disclaimer of Liability

Technical information contained herein is furnished without charge or obligation and is given and accepted at recipient’s sole risk. Because conditions of use may vary and are beyond our control, Owens Corning makes no representation about and is not responsible or liable for the accuracy or reliability of data associated with particular uses of any product described herein. SCS Global Services provides independent verification of recycled content in building materials and verifies recycled content claims made by manufacturers. For more information, visit www.SCSglobalservices.com.

LEED® is a registered trademark of the U.S. Green Building Council.

Notes

Not for use in roofing. For roofing applications, use FOAMULAR® THERMAPINK® XPS insulation.

For additional information, refer to the Safe Use Instruction Sheet (SUIS) found in the SDS Database via <http://sds.owenscorning.com>.

Product and Packaging Data

MATERIAL		PACKAGING							EDGES
THICKNESS (IN)	PRODUCT DIMENSIONS THICKNESS X WIDTH X LENGTH (IN)	PALLET (UNIT) DIMENSIONS (TYPICAL) WIDTH X LENGTH X HEIGHT (FT)	SQUARE FT. PER PALLET	BOARD FT. PER PALLET	BUNDLES PER PALLET	PIECES PER BUNDLE	PIECES PER PALLET		
¾	¾ x 24 x 96 (half unit)	4 x 8 x 4	1,920	1,536	4	30	120	Square Edge	
	¾ x 48 x 96 (half unit)	4 x 8 x 4	1,920	1,536	2	30	60	Scored Square Edge	
1	1 x 24 x 96	4 x 8 x 4	1,536	1,536	8	24	96	Tongue & Groove	
	1 x 48 x 96	4 x 8 x 8	3,072	3,072	8	12	96		
	1 x 48 x 96 (half unit)	4 x 8 x 8	1,536	1,536	4	12	48		
	1 x 48 x 108	4 x 9 x 8	3,456	3,456	8	12	96		
1½	1.5 x 24 x 96	4 x 8 x 8	2,048	3,072	8	16	128		
	1.5 x 48 x 96	4 x 8 x 8	2,048	3,072	8	8	64		
2	2 x 24 x 96 (half unit)	4 x 8 x 4	768	1,536	4	12	48		
	2 x 24 x 108	4 x 9 x 8	1,728	3,456	8	12	96		
	2 x 48 x 96	4 x 8 x 8	1,536	3,072	8	6	48		
2½	2.5 x 24 x 96	4 x 8 x 8	1,152	2,880	8	9	72		
	2.5 x 48 x 96	4 x 8 x 8	1,152	2,880	4	9	36		
3	3 x 24 x 96	4 x 8 x 8	1,024	3,072	8	8	64		
	3 x 48 x 96	4 x 8 x 8	1,024	3,072	8	4	32		
4	4 x 24 x 96	4 x 8 x 8	768	3,072	8	6	48		
	4 x 48 x 96	4 x 8 x 8	768	3,072	8	3	24		

Available lengths and edge configurations vary by thickness. Other sizes may be available upon request. Consult your local Owens Corning representative for availability.

Limited Warranty

FOAMULAR® & FOAMULAR® NGX™ XPS insulation limited lifetime warranty maintains 90% of its R-value for the lifetime of the building and covers all ASTM C578 properties. See [FOAMULAR® Extruded Polystyrene Insulation Lifetime Limited Warranty](#) for complete details, limitations, and requirements.

OWENS CORNING FOAM INSULATION, LLC
ONE OWENS CORNING PARKWAY
TOLEDO, OHIO 43659 USA

1-800-GET-PINK®
www.owenscorning.com