

PROCAT® HIGH PERFORMANCE LOOSEFILL INSULATION FOR THE PRO



ProCat® Insulation is a loosefill fiberglas™ thermal insulation. It is designed for use exclusively with the ProCat® machine.

Features

 The ProCat® machine has a "dense mode" setting to enable installation of ProCat® insulation at higher R-value in the eaves, where height may be limited

Applications

- ProCat® Insulation is intended for use in both "open" applications, such as the floor of vented attics, and in "closed cavity" applications, such as walls and floors between stories of a house
- ProCat® Insulation can be used in both existing and new construction

Standards, Code Compliance

- ProCat® Insulation conforms to the product requirements of ASTM C764 Type I (pneumatic application)
- R-values are determined in accordance with ASTM C687.
- Passes the requirements of ASTM E136 and is considered non-combustible insulation by the model building codes.
- The surface burning characteristics of this product have been determined in accordance with:

	ULC S 102.2	ASTM E84 ¹
Flame Spread	0	0
Smoke Developed	5	5

- ProCat[®] Insulation is non-corrosive (per ASTM C764, section 12.8)²
- Does not absorb moisture (per ASTM C1104)
- Does not support mold growth (per ASTM C1338)
- · Conforms to the quality standards of the State of California
- Meets requirements of Minnesota Insulation Standards Program

Design Considerations

To help prevent fire or overheating of recessed light fixtures or similar electrical devices, do not insulate on top of or within 3 inches of such devices unless they are specifically approved and labeled "IC rated" (insulation contact).

Do not place insulation in air spaces surrounding metal flues, chimneys, or fireplaces. Provide minimum clearances specified in NFPA-31, NFPA-54, or NFPA-211, or as required by local building codes.

Installation

Stated R-value is achieved by installing the minimum required number of bags per 1,000 net sq. ft. at a thickness not less than the label minimum thickness. Failure by the installer to provide both the required number of bags and at least the minimum thickness will result in lower insulation R-value.

In order to achieve the R Values stated on this data sheet, strictly follow Owens Corning's written instructions and recommendations for the operation, maintenance and service of the ProCat® machine.

Owens Corning does not recommend or approve blending or adding additional materials or adhesives to this product during installation. Owens Corning will accept no responsibility or liability when the product is not installed in accordance with the product label and installation instructions.

Owens Corning recommends and provides instructions for installing ProCat® Insulation from the outside of exterior sidewalls. You may also install it from the inside, however, it is important to note that drill and fill installation from the inside requires a strong working knowledge of construction and framing principles, texture matching and other variables. Please consult a professional contractor to perform this job if you do not have this expertise.

¹ This standard is used to measure and describe the response of materials, products, or assemblies to heat and flame under controlled conditions, but does not by itself incorporate all factors required for fire-hazard or fire-risk assessment of the materials, products, or assemblies under actual fire conditions. However, the results of these tests may be used as elements of a fire risk assessment that takes into account all of the factors pertinent to an assessment of the fire hazard of a particular end use. Values are reported to the nearest five (5) rating.

² Based on ASTM C764, section 12.8 uses the C1617 analytical repeatable test.

PROCAT®

Net Weight 33.5 lbs.

R-VALUE	BAGS PER 1000 SQ. FT.	MAXIMUM NET COVERAGE, SQ. FT.	MINIMUM WEIGHT/ SQ. FT.	MINIMUM INITIAL INSTALLED THICKNESS INCHES	MINIMUM SETTLED THICKNESS, INCHES
13	5.1	198.0	0.169	4.75	4.75
19	7.8	128.7	0.260	7.00	7.00
22	9.0	110.6	0.303	8.00	8.00
26	10.7	93.5	0.358	9.25	9.25
30	12.4	80.6	0.416	10.50	10.50
38	16.4	60.9	0.550	13.25	13.25
44	19.1	52.3	0.641	15.00	15.00
49	21.5	46.4	0.722	16.50	16.50
60	27.1	36.9	0.908	19.75	19.75

PROCAT® WALLS

Net Weight 33.5 lbs.

R-VALUE	FRAMING	MINIMUM INITIAL INSTALLED THICKNESS (IN.)	INSTALLED DENSITY (LBS. PER CU. FT.)	MAXIMUM COVERAGE PER BAG (SQ. FT.)	MINIMUM BAGS PER 1,000 SQ. FT.	MINIMUM WEIGHT (LBS. PER SQ. FT.)
14	2x4	3.5	1.30	84.4	11.8	0.379
15	2x4	3.5	1.50	73.1	13.7	0.438
22	2x6	5.5	1.30	53.7	18.6	0.596
23	2x6	5.5	1.50	46.5	21.5	0.688
24	2x6	5.5	1.90	36.7	27.2	0.871

PROCAT® DENSE

Net Weight 33.5 lbs.

	ADDITIONAL BAGS REQUIRED PER 100 FT OF ROOF LINE			
R-VALUE	4:12 ROOF PITCH	5:12 ROOF PITCH	6:12 ROOF PITCH	
30	1.2	1	0.8	
49	3.6	3	2.4	
60	5.5	4.5	3.6	

TECHNICAL DATA

PROPERTY (UNIT)	VALUE	TEST
Thermal resistance	(See coverage charts)	ASTM C518 & ASTM C687
Surface Burning Characteristics		
flame spread / smoke	0/5	ASTM E84 ³
developed	0/5	Can/ULC S102.2
Critical Radiant Flux (W/cm²)	>0.12	ASTM E970
Combustion characteristics	Noncombustible	ASTM E136
Water Vapor Sorption (by weight)	<5%	ASTM C1104/C1104M
Odor Emission	Pass	ASTM C1304
Corrosion Resistance	Pass	ASTM C764, Section 12.84
Fungi resistance	Pass	ASTM C1338

³ This standard is used to measure and describe the response of materials, products, or assemblies to heat and flame under controlled conditions, but does not by itself incorporate all factors required for fire-hazard or fire-risk assessment of the materials, products, or assemblies under actual fire conditions. However, the results of these tests may be used as elements of a fire risk assessment that takes into account all of the factors pertinent to an assessment of the fire hazard of a particular end use. Values are reported to the nearest five (5) rating.

Certifications and Sustainable Features

 Certified to meet indoor air quality standards under the stringent GREENGUARD Indoor Air Quality Certification Program[™], and the GREENGUARD Gold Certification.*







Disclaimer of Liability

Technical information contained herein is furnished without charge or obligation and is given and accepted at recipient's sole risk. Because conditions of use may vary and are beyond our control, Owens Corning makes no representation about, and is not responsible or liable for the accuracy or reliability of data associated with particular uses of any product described herein. GREENGUARD Certified products are certified to GREENGUARD standards for low chemical emissions into indoor air during product usage. For more information, visit ul.com/gg. This Home Innovation Research Labs Green Approved mark is your assurance that a product is eligible for points toward National Green Building Certification. Visit www.GreenApprovedProducts.com for details.



Owens Corning Insulating Systems, LLC

One Owens Corning Parkway Toledo, OH 43659 USA

1-800-GET-PINK® www.owenscorning.com

Pub. No. 10019483-H. Printed in U.S.A. May 2025. THE PINK PANTHER™ & © 1964−2025 Metro-Goldwyn-Mayer Studios Inc. All Rights Reserved. The color PINK is a registered trademark of Owens Corning. © 2025 Owens Corning. All Rights Reserved.

⁴ Based on ASTM C764, section 12.8 uses the C1617 analytical repeatable test.