




# FOAMULAR® Cel-Lok® Extruded Polystyrene (XPS) Rigid Foam Board Insulation



## PRODUCT FEATURES

### Description

Extruded polystyrene (XPS) rigid insulation board with three double grooves per board for insertion of U shaped metal furring strip.

### Basic Uses/Related Uses

Continuous insulation for concrete or concrete block walls applied directly to the wall surface to yield a reduction in total thickness of the assembly. Once furring strips are inserted, they are fastened to concrete or concrete masonry unit walls using pilot hole-concrete screws; metal furring channels are used to hold insulation in place and as fastening base for finishing material that must be an approved thermal barrier, as required by the applicable building Code. For exterior applications the zinc coating is not sufficient corrosion protection for the metal channels.

### Selection Criteria

- Thermal resistance of R5 per inch<sup>†</sup>
- Thermal resistance and surface to secure thermal barrier when space is limited
- Moisture resistant (hydrophobic), long term durability
- Saw, cut or score to size

### Sustainability Criteria

- Recycled content of 20%, pre-consumer (SCS Global Services)
- UL GREENGUARD Gold Certification
- Product specific Type 3 UL Environmental Product Declaration and Transparency Brief
- Silver Material Health Certification (Cradle to Cradle Products Innovation Institute)
- Contributes to credits in green building programs such as LEED® and Green Globes. For further information see documents: LEED® v4 for Building Design and Construction and Owens Corning Impact Study - Leadership in Energy and Environmental Design (LEED® v4).



## Applicable Standards

<b>CAN/ULC-S701</b>	Standard for Thermal Insulation, Polystyrene Boards
<b>CAN/ULC-S102.2</b>	Standard Method of Test for Surface Burning Characteristics of Flooring, Floor Coverings and Miscellaneous Materials and Assemblies
<b>ASTM C177</b>	Standard Test Method for Steady-State Heat Flux Measurements and Thermal Transmission Properties by Means of the Guarded-Hot-Plate
<b>ASTM C203</b>	Standard Test Method for Breaking Load and Flexural Properties of Block-Type Thermal Insulation
<b>ASTM C518</b>	Standard Test Method for Steady-State Thermal Transmission Properties by Means of the Heat Flow Meter Apparatus
<b>ASTM E228</b>	Standard Test Method for Linear Thermal Expansion of Solid Materials with a Push-rod Dilatometer
<b>ASTM D1621</b>	Standard Test Method for Compressive Properties of Rigid Cellular Plastics
<b>ASTM D2126</b>	Standard Test Method for Response of Rigid Cellular Plastics to Thermal and Humid Aging
<b>ASTM D2842</b>	Standard Test Method for Water Absorption of Rigid Cellular Plastics
<b>ASTM E96</b>	Test Methods for Water Vapour Transmission of Materials

## Performance Criteria

<b>Compliance:</b>	Evaluation Listing No. 13431-L Type 3	CCMC CAN/ULC-S701
<b>Physical Properties:</b>	Compressive Strength <sup>1</sup> : <b>20 psi (140 kPa)</b> Compressive Modulus: <b>1000 psi (6895 kPa)</b> Flexural Strength: <b>70 psi (483 kPa)</b> Dimensional Stability, Maximum, % linear change: <b>1.5</b> Linear Coefficient of Thermal Expansion: <b>3.5 x 10<sup>-5</sup> in./in./°F (6.3 x 10<sup>-5</sup> mm/mm/°C)</b>	ASTM D1621 ASTM D1621 ASTM C203 ASTM D2126  ASTM E228
<b>Thermal:</b>	R5 ft <sup>2</sup> hr <sup>2</sup> F/BTU per inch (RSI 0.88 m <sup>2</sup> C/W per 25 mm)	ASTM C518 or C177
<b>Moisture:</b>	Water Absorption, (max. % by volume): <b>0.70</b> Water Vapour Permeance: <b>0.90 Perm (52 ng/Pas.m<sup>2</sup>)</b> Water Capillarity: <b>None</b> Water Affinity: <b>Hydrophobic</b> Limiting Oxygen Index, min.: <b>24</b>	ASTM D2842 ASTM E96 - - ASTM D2863
<b>Fire:</b>	Combustible Flame spread 90; smoke developed >350 Max. Service Temp. 165 °F (74 °C)	CAN/ULC-S114 CAN/ULC-S102.2 -

<sup>1</sup>10% deformation or yield, whichever occurs first

## Delivery and Storage

Deliver products in their original packages, and store in enclosed shelter. Packaging is not UV resistant. Shelter unused packages from the elements.

<sup>†</sup>The LTR performance for Owens Corning FOAMULAR® insulation products per CAN/ULC S701-17 are as follows: Type 3 products: Minimum LTR of RSI 1.62 at 50 mm thickness & Type 4 products: minimum LTR of RSI 1.66 at 50 mm thickness. Please consult local Owens Corning Technical Representative.



# FOAMULAR® Cel-Lok®

## Extruded Polystyrene (XPS)

### Rigid Foam Board Insulation

#### Limitations

- Exposure to exterior conditions during normal construction cycles is permitted. During that time some fading of color may begin due to UV exposure, and, if exposed for extended periods of time, some degradation or “dusting” of the polystyrene surface may begin. It is best if the product is covered within 60 days to minimize degradation. Once covered, the deterioration stops, and damage is limited to the thin top surface layers of cells. Cells below are generally unharmed.
- This product is combustible. A protective barrier or thermal barrier is required to separate this product from interior living or conditioned spaces as specified in the appropriate building code.
- FOAMULAR® XPS insulation limited lifetime warranty maintains 90% of its thermal resistance for the lifetime of the building and covers all CAN/ULC -S701.
- Prior to use of adhesives, sealants or other similar products with polystyrene boards, verify their compatibility with adhesive manufacturers.

#### Sizes

Thickness	Widths	Lengths	Edges
FOAMULAR® Cel-Lok® XPS			
38 mm, 51 mm (1.5", 2")	610 mm (24")	2438 mm (96")	Ship Lapped

FOAMULAR® Cel-Lok® is shipped in units containing four individually shrink-wrapped packages.

#### Safety

This product is combustible and may constitute a fire risk if not used or installed properly. Although it contains a fire-suppressing agent, the product will ignite if exposed to a sufficiently intense flame. Do not expose to open flames or any other ignition source during transport, handling, storage or use. For additional information refer to Safe Use Instruction Sheet (SUIS) found in the SDS Database via <http://sds.owenscorning.com>.

#### PRODUCT PLACEMENT

##### Installation

Insert metal furring strips and fasten to concrete or concrete block walls using a pilot hole-concrete screw (min. penetration of 25 mm (1 in.) and min. 4 screws per length of metal furring channel). Metal furring channels are used to hold insulation in place and as fastening base for finishing material that must be an approved thermal barrier, as required by the applicable building Code. For exterior applications the zinc coating is not sufficient corrosion protection for the metal channels.

Consult an Owens Corning Canada Technical representative for appropriate fastener and adhesive selections.

##### Technical Services Available

For Canadian Technical inquiries please contact local representative. See Technical territory map via [www.specowenscorning.ca/contacttech](http://www.specowenscorning.ca/contacttech).

Current Ed: 2018.09.01  
Previous Ed: 2018.09.01

#### Disclaimer of Liability

Technical information contained herein is furnished without charge or obligation and is given and accepted at recipient's sole risk. Because conditions of use may vary and are beyond our control, Owens Corning makes no representation about, and is not responsible or liable for the accuracy or reliability of data associated with particular uses of any product described herein.

SCS Global Services provides independent verification of recycled content in building materials and verifies recycled content claims made by manufacturers. For more information, visit [www.SCSglobalservices.com](http://www.SCSglobalservices.com).

LEED® is a registered trademark of the U.S. Green Building Council.



**OWENS CORNING CANADA LP**  
3450 MCNICOLL AVENUE  
SCARBOROUGH, ONTARIO M1V 1Z5  
**1-800-GET-PINK®**  
[www.owenscorning.ca](http://www.owenscorning.ca)

Pub. No. 501126. Printed in Canada. September 2018.  
THE PINK PANTHER™ & © 1964–2018 Metro-Goldwyn-Mayer Studios Inc.  
All Rights Reserved. The colour PINK is a registered trademark of Owens Corning.  
© 2018 Owens Corning. All Rights Reserved.

