



RHINOWRAP™ 125

A high strength reinforcing high density polyethylene scrim coated two sides with a uniquely engineered low density black polyethylene blend.

PRODUCT SPECIFICATIONS

Nominal Weave	8 x 8 ppi
Coating	Two Sides LDPE @ 1-1.2 mil thickness
Color	Black, White, Blue, White
Weight	118 g/m ² ± 5% (3.5 oz/yd ² ± 5%) finished weight
Widths	Up to 144"



TENSILE STRENGTH ASTM D751

Machine Direction	Force	110 lbs.	50 kg
	20% Elongation		
Cross Direction	Force	110 lbs.	50 kg
	20% Elongation		

TRAPEZOIDAL TEAR STRENGTH ASTM D4533

Machine Direction	Force	40 lbs.	18 kg
Cross Direction	Force	40 lbs.	18 kg

UV ACCELERATED WEATHERING ASTM G154 (More than 90% strength retained after 2,000 hours* exposure)

Mullen Burst ASTM D751	180 psi	1241 kPa
Nominal Thickness	6 mils	0.15 mm

Note: all values are ± 10% * QUV A-340 lamps 8 hrs UV @ 60° C, 4 hrs condensation @ 40° C
The test data is based on an average taken over several production runs and should not be considered or interpreted as minimum or maximum values.
Values are typical data and not limiting specifications.

Effective Date: January, 2018

800.567.9727
geosynthetics@owenscorning.com

www.owenscorning.com/geosynthetics