



TECHNICAL BULLETIN

FOAMULAR® & FOAMULAR® NGX™

EXTRUDED POLYSTYRENE (XPS) INSULATION

ASTM C578 — TYPES AND PHYSICAL PROPERTIES

This table outlines the basic physical property requirements of ASTM C578¹ and FOAMULAR®/FOAMULAR® NGX™ XPS insulation compliance. The products are organized, left to right, in ascending compressive strength. For complete details on board types, properties and other quality requirements, see the actual ASTM standard.

POLYSTYRENE BOARD TYPE ²	EPS	EPS	EPS	FOAMULAR®/FOAMULAR® NGX™ 150, XPS	EPS	FOAMULAR®/FOAMULAR® NGX™ 250, XPS	EPS	FOAMULAR®/FOAMULAR® NGX™ 400, XPS	EPS	FOAMULAR®/FOAMULAR® NGX™ 600, XPS	EPS	FOAMULAR®/FOAMULAR® NGX™ 1000, XPS
ASTM C578 Classification Type	XI	I	VIII	X	II	IV	IX	VI	XIV	VII	XV	V
Compressive resistance at yield or 10 % deformation, whichever occurs first (with skins intact) min, psi (kPa)	5.0 (35)	10.0 (69)	13.0 (90)	15.0 (104)	15.0 (104)	25.0 (173)	25.0 (173)	40.0 (276)	40.0 (276)	60.0 (414)	60.0 (414)	100.0 (690)
Density, min, lb/ft ³ (kg/m ³)	0.70 (12)	0.90 (15)	1.15 (18)	1.30 (21)	1.35 (22)	1.55 (25)	1.80 (29)	1.80 (29)	2.40 (38)	2.20 (35)	2.85 (46)	3.00 (48)
Thermal resistance of 1.00-in. (25.4-mm) thickness, min, hr·ft ² ·°F/Btu (K·m ² /W) Mean temperature: 75±2° (24±1°C)	3.10 (0.55)	3.60 (0.63)	3.80 (0.67)	5.00 (0.88)	4.00 (0.70)	5.00 (0.88)	4.20 (0.74)	5.00 (0.88)	4.20 (0.74)	5.00 (0.88)	4.30 (0.76)	5.00 (0.88)
Flexural strength, min, psi (kPa)	10.0 (70)	25.0 (173)	30.0 (208)	40.0 (276)	35.0 (240)	50.0 (345)	50.0 (345)	60.0 (414)	60.0 (414)	75.0 (517)	75.0 (517)	100.0 (690)
Water vapor permeance of 1.00-in. (25.4-mm) thickness, max, perm (ng/Pa·s·m ²)	5.0 (287)	5.0 (287)	3.5 (201)	1.5 (86)	3.5 (201)	1.5 (86)	2.5 (143)	1.1 (63)	2.5 (143)	1.1 (63)	2.5 (143)	1.1 (63)
Water absorption by total immersion, max, volume	4.0	4.0	3.0	0.3	3.0	0.3	2.0	0.3	2.0	0.3	2.0	0.3

1 ASTM C578-10, "Standard Specification for Rigid, Cellular Polystyrene Thermal Insulation"; published by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959

2 XPS is extruded polystyrene. EPS is expanded polystyrene, also known as molded polystyrene.

Disclaimer of Liability

Technical information contained herein is furnished without charge or obligation and is given and accepted at recipient's sole risk. Because conditions of use may vary and are beyond our control, Owens Corning makes no representation about, and is not responsible or liable for the accuracy or reliability of data associated with particular uses of any product described herein. Nothing contained in this bulletin shall be considered a recommendation.

OWENS CORNING FOAM INSULATION, LLC
 ONE OWENS CORNING PARKWAY
 TOLEDO, OHIO 43659 USA
1-800-GET-PINK®
www.owenscorning.com