



RhinoMat® 750 a 30 mil (0.75 mm) thick, polyethylene Reinforced Composite Geomembrane (RCG), specifically designed for use in water retention and containment applications to **Weld Easier. Install Faster. Contain Better.**™ For applications where retention and containment are critical, the durable, stress crack resistant, lightweight construction of RhinoMat® 750 provides maximum performance in many different climates and environmental conditions.

RhinoMat® 750 Applications:

Containment:

- Agriculture & Aquaculture
- Mining & Energy
- Secondary Containment
- Wastewater Lagoons
- Landfill Covers

Retention:

- Golf Course Ponds
- Stormwater Management
- Irrigation Storage
- Canal Liners
- Potable Water Reservoirs

RhinoMat® 750 conforms to the properties below, and is manufactured at an Owens Corning facility having achieved ISO 9001:2000 certification. Owens Corning tests RhinoMat® 750 both through independent, third party laboratories, and through internal quality control testing in laboratories accredited through the Geosynthetic Accreditation Institute – Laboratory Accreditation Program (GAI-LAP).

PROPERTY	TEST/METHOD	TYPICAL VALUE ¹		MIN AVE. ROLL VALUE ²	
		English	Metric	English	Metric
Weight	ASTM D5261	18 oz./yd ²	610 g/m ²	17.1 oz./yd ²	581 g/m ²
Thickness	ASTM D751	33.5 mil	0.85 mm	30 mil	0.76 mm
Strip Tensile Strength (MD)	ASTM D7003	246 lbf	1094 N	224 lbf	996 N
Strip Tensile Strength (CD)	ASTM D7003	272 lbf	1210 N	262 lbf	1165 N
Strip Tensile Elongation (MD)	ASTM D7003	21%			
Strip Tensile Elongation (CD)	ASTM D7003	21%			
Tongue Tear (MD)	ASTM D5884	56 lbf	249 N	50 lbf	222 N
Tongue Tear (CD)	ASTM D5884	56 lbf	249 N	50 lbf	222 N
CBR Puncture	ASTM D6241	1348 lbf	5996 N	1301 lbf	5787 N
Index Puncture Resistance	ASTM D4833	230 lbf	1023 N	199 lbf	885 N
Hydrostatic Resistance	ASTM D751	729 lb/in ²	5026 kPa	705 lb/in ²	4861 kPa
Dimensional Stability ³	ASTM D1204	1.52%			
Water Vapor Transmission ³	ASTM E96	0.09 g/m ² day			
UV Resistance (Fluorescent Light Method) ⁴	ASTM D7238				
a) Strength & Elongation retained after 10,000 light hours	ASTM D7003	> 90% retained		> 90% retained	
b) Response to bending	GRI GM-16	no cracking		no cracking	
Grab Tensile Strength (MD)	ASTM D751	385 lbf	1713 N		
Grab Tensile Strength (CD)	ASTM D751	385 lbf	1713 N		
Trapezoidal Tear (MD)	ASTM D4533	66 lbf	294 N		
Trapezoidal Tear (CD)	ASTM D4533	66 lbf	294 N		
Seam Strength (Shear) ⁵	ASTM D7747	100 lbf	445 N		
Seam Strength (Peel) ⁶	ASTM D7747	25 lbf	111 N		
Hydraulic Conductivity	ASTM E96 ('B')	1.0 x 10 ⁻¹⁴ cm/sec			
Carbon Black Content	ASTM D4218	> 2%			
Accelerated UV Weathering ⁷	ASTM G154	> 90% @ 10,000 hrs.			
Low Temperature Brittleness	ASTM D2136	Pass (@ -60°F)	Pass (@ -51°C)		
Standard Roll Width		12 ft	3.7 m		
Standard Roll Length		1500 ft	457 m		
Approximate Roll Weight		2200 lb	998 kg		

Effective Date: June 1, 2017

Notes:

- ¹Typical values represent an average test result for the sample size, with + 10% variance
- ²Minimum Average Roll Values (MARV) are shown (unless otherwise noted), in accordance with GRI-GM30
- ³Dimensional Stability and Water Vapor Transmission values shown are maximum test result values
- ⁴Test samples were exposed to UV radiation using this method prior to evaluating changes in material properties
- ⁵Test values reflect single-track wedge welding at approximately 750° F and 14 ft/sec
- ⁶Test values reflect single-track wedge welding at approximately 750° F and 14 ft/sec
- ⁷Test valued based on A-340 lamps, 8 hours UV @ 60° C, 4 hours condensation @ 40° C

This publication should not be construed as engineering advice. While information contained in this publication is accurate to the best of our knowledge, Owens Corning does not warrant its accuracy or completeness. The user of the products should assume sole responsibility for the final determination of the suitability of the information and the products for the contemplated and actual use. Owens Corning specifically disclaims all warranties, express or implied, including without limitation, warranties of merchantability or fitness for a particular purpose, or arising from provision of samples, a course of dealing or usage of trade.

Contact your RhinoMat® Sales Representative at:

Toll Free: 800.567.9727 | Email: RhinoMat@OwensCorning.com
OwensCorning.com/RhinoMat

© 2017 Owens Corning. All Rights Reserved.

Pub. No. 10021425-C
 RM750_TDS
 July 2017



WELD EASIER. INSTALL FASTER. CONTAIN BETTER.™

For water retention, containment, aquaculture,
 pond and canal lining applications

GRI-GM30
 COMPLIANT

BE WATER SMART.

RhinoMat® 750 is a 30 mil (0.75 mm) geomembrane specifically designed for use in water retention and containment applications to **Weld Easier. Install Faster. Contain Better.**™ For applications where containment is critical, the durable, stress crack resistant, lightweight construction of RhinoMat® geomembrane provides maximum performance in all climates and environmental conditions.

RhinoMat® 750 is a Smart Choice

Features Strong Construction

- A 30 mil (0.75 mm) geomembrane
- Inner woven core layer provides dimensional stability with impressive tensile and tear strength
- Puncture, abrasion and chemical resistant construction
- Outstanding hydrostatic resistance
- All layers contain UV protection

Meets Industry Standards


- GRI-GM30 Compliant – RhinoMat is the first portfolio of products to meet this standard
- Non-toxic, no PVC or other hazardous materials used in the construction of the geomembrane
- Impressive UV, ozone and oxidation resistance

Provides Warranty Protection

- Standard warranty: 20-years buried, 10-years exposed
- Available special registered warranty (clear water applications): 25-years buried, 20-years exposed



ENGINEERED LLDPE/LDPE COATING
For flexibility, chemical resistance and protection against UV, ozone and oxidation



HDPE HIGH STRENGTH WOVEN CORE
For outstanding dimensional strength and stability

SurFlex™

UV resistant SurFlex™ technology provides excellent welding characteristics, reduces stress cracking and makes it easy to seam in the factory or field

WELD EASIER.



- Made with SurFlex™ technology, a polyolefin blend surface film which allows for superior thermal fusion welding
- Designed for optimal welding temperature and speed to create exceptional seams
- Flexible construction enables efficient seaming of a wide variety of panel shapes and sizes

INSTALL FASTER.



- Wide width flexible sheets facilitate factory fabrication to reduce field seaming time
- Factory fabricated seaming capability ensures higher quality welds which require fewer time-consuming destructive field tests
- Allows for large factory fabricated panels to be customized to accelerate project field installation

CONTAIN BETTER.



- High strength woven core and engineered coatings provide outstanding longevity and chemical resistance
- Meets or exceeds properties of Category 1 (Severe) of the GRI-GM30 specification from the Geosynthetic Institute (GSI)
- Hydrostatic, puncture, and abrasion resistance stands up to the toughest installation, maintenance and environmental stresses

